IC4CRCV FW

超硬4枚刃ミニチュアコーナーラウンジングカッター

Coated Solid Carbide 4-flute Miniature Corner R Cutter

R面取り加工の決定版!!











生材から高硬度鋼まで 幅広い加工領域!!

超微粒子超硬+TiSiN にて 高剛性で耐摩耗性にも優れ 長寿命!!

非常に薄いワークも 加工可能!!



単位:mm

商品コード Item Code	R±0.02	D±0.1	Q	L	d	標準価格 Price
IC4CRCV 0.25R	0.25	1	6	50	3	10,600
IC4CRCV 0.3R	0.3	1	6	50	3	10,600
IC4CRCV 0.4R	0.4	1	6	50	3	10,600
IC4CRCV 0.5R	0.5	1.5	8	50	4	9,400
IC4CRCV 0.6R	0.6	1.5	8	50	4	8,600
IC4CRCV 0.7R	0.7	1.5	8	50	4	8,600
IC4CRCV 0.8R	0.8	1.5	8	50	4	8,600
IC4CRCV 0.9R	0.9	1.5	8	50	4	8,600
IC4CRCV 1.0R	1.0	1.5	8	50	4	9,400
IC4CRCV 1.25R	1.25	2	9	50	6	9,500
IC4CRCV 1.5R	1.5	2	9	50	6	9,500
IC4CRCV 1.75R	1.75	2	9	50	6	9,500
IC4CRCV 2.0R	2.0	2.5	10	50	8	10,700
IC4CRCV 2.25R	2.25	2.5	10	50	8	10,700
IC4CRCV 2.5R	2.5	2.5	10	50	8	10,700


■標準切削条件表 Recommended cutting conditions

■标华见	削米件衣	Recommended cu	itung conditions								
被削材 WORK		炭素鋼/鋳 S50C/FC250/S	鉄/合金鋼 SCM(HRC≦30)	合金鋼/ SKD61/SK/NA	/工具鋼 K (HRC30~45)		レス鋼 /SUS316	焼入れ鋼/調質鋼 Hardened Steel (HRC45~55)			
R	d	切削速度 Vc(m/min)	送り速度 fz(mm/t)	切削速度 Vc(m/min)	送り速度 fz(mm/t)	切削速度 Vc(m/min)	送り速度 fz(mm/t)	切削速度 Vc(m/min)	送り速度 fz(mm/t)		
0.25 0.3 0.4	3	30~50	0.007~0.015	15~30	0.007~0.015	10~20	0.007~0.015	10~15	0.007~0.015		
0.5 0.6 0.7 0.8 0.9 1.0	4	30~50	0.010~0.025	15~30	0.010~0.025	10~20	0.010~0.025	10~15	0.010~0.025		
1.25 1.5 1.75	6	30~50	0.018~0.035	15~30	0.018~0.035	10~20	0.018~0.035	10~15	0.018~0.035		
2.0 2.25 2.5	8	30~50	0.025~0.060	15~30	0.025~0.060	10~20	0.025~0.060	10~15	0.025~0.060		
Depth	み量 of cut		ap≦R	R+0.1D	_	ap≦R+0.05D					

※切削条件はあくまでも目安です。使用される機械、チャックの剛性や切削油等の状況によって変動致します。 ※切削除の使用を推奨いたします。 ※荒加工と仕上げ加工等、切込みは数回に分けて加工してください。

■加工範囲の目安

R	0.25	0.3	0.4	0.5	0.6	0.7	0.8	0.9	1.0	1.25	1.5	1.75	2.0	2.25	2.5
d		3		4				6			8				
Α	0.52	0.55	0.59	0.73	0.66	0.57	0.49	0.41	0.31	0.80	0.59	0.38	0.86	0.65	0.44
В	0.94	0.95	0.95	1.19	1.20	1.21	1.22	1.22	1.22	1.93	1.95	1.97	2.67	2.69	2.71
C	1.00	1 00	1 00	1 25	1 25	1 25	1 25	1 25	1 25	2.00	2.00	2.00	2.75	2.75	2.75







ホームページはこちら

工具鋼/ブリハードン鋼 合金鋼/ステンレス鋼 SKD, NAK101 SCM, SUS304 熱処理鋼等 Hardened Steels 構造用鋼/炭素鋼 SS41, S45C 硬質材 Hard material HRC30-35 HRC≦30 HRC35-40 HRC40-45 HRC45-55

























取扱い販売店

総販売元 **2 れー**知 **と**は **は 込 大 と MARUICHI CUTTING TOOLS CO.,LTD.**

http://www.thecut.co.jp

e-mail: info-thecut@thecut.co.jp